

Silirub+ S8800

Revision: 2/08/2013

Page 1 from 2

Technical data

Basis	Polysiloxane
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (20°C / 65% R.H.)	Ca. 10 min
Curing speed * (20°C / 65% R.H.)	Ca. 2 mm/24h
Hardness	25 ± 5 Shore A
Density	1,03 g/ml
Elastic recovery (ISO 7389)	> 80 %
Maximum allowed distortion	25 %
Temperature resistance	-60 °C → 180 °C
Max. tension (DIN 53504)	2,00 N/mm ²
Elasticity modulus 100% (DIN 53504)	0,45 N/mm ²
Elongation at break (DIN 53504)	700 %
Application temperature	5 °C → 35 °C

(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

Product description

Silirub+ S8800 is a high-quality, neutral, elastic one-component silicone based joint sealant.

Properties

- No staining on porous surfaces such as marble, granite and other natural stones
- Very easy to apply
- No filamenting - can be shaped and finished very well
- Colourfast and UV resistant
- Weatherproof
- Permanent elastic after curing
- Corrosion free
- Impervious to mould, contains ZnP (biocide with fungicidal action)
- Excellent adhesion on glass, ceramic, enamel and galvanised metals
- 25% maximum allowed distortion
- Solvent, halogen, acid and isocyanate free.
- Resistant against usual household cleaners and disinfectants

Applications

- Sealing applications on natural stone such as marble, granite, etc. In sanitary areas and kitchens.
- Joints between facade elements, doors, etc. of natural stone in general construction applications.

Packaging

Colour: transparent, white, black, joint grey, manhattan, anthracite, jasmine, dust grey, medium grey, transparent-grey, bright beige, marblegrey, bahamabeige
Packaging: 310 ml cartridge

Shelf life

18 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Silirub+ S8800

Revision: 2/08/2013

Page 2 from 2

Substrates

Substrates: Specially developed for use on natural stoen (marble, granite, blue stone, etc..), all usual building substrates, ceramic tiles, aluminium, metals, enamel, glass, ...

Nature: clean, dry, free of dust and grease.

Surface preparation: Porous surfaces in water loaded applications should be primed with Primer 150. All smooth surfaces can be treated with Surface Activator.

While producing plastics very often releasing agents, processing aids and other protective agents (like protection foil) are used. These should be removed prior to bonding. There is no adhesion on PE, PP, PTFE (Teflon®), silicones and bituminous substrates. We recommend a preliminary compatibility test.

- The sanitary formula should not replace regular cleaning of the joint. Excessive contamination, deposits or soap remainigs will stimulate the development of fungi.

Standards

- ISO 11600 F 25LM
- DIN 18545 - 2

Joint dimensions

Min. width for joints: 5 mm

Max. width for joints: 30 mm

Min. depth for joints: 5 mm

Recommendation sealing jobs: joint width = 2 x joint depth.

Application method

Application method: With manual- or pneumatic caulking gun.

Cleaning: Clean with white spirit or Surface Cleaner immediately after use.

Finishing: With a soapy solution or Soudal Finishing Solution before skinning.

Repair: With the same material

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult the packaging label for more information.

Remarks

- Contact with bitumen, tar or other plasticizer releasing materials such as EPDM, neoprene, butyl, etc. is to be avoided since it can give rise to discolouration and loss of adhesion.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.